

Southbank


- Stone effect
- Suitable for walls + floors
- Neutral tones

5
COLOURS

4
FINISHES

8
TILE SIZES

GRESTEC.CO.UK / 0345 130 2241



IMQ44967 LRV: 48 IMQ44968 LRV: 34 IMQ44969 LRV: 30 IMQ44970 LRV: 18 IMQ44971 LRV: 12

HOL 6 - 1200x2600 ONLY




IMQ44967HOL-6 IMQ44968HOL-6 IMQ44969HOL-6 IMQ44970HOL-6 IMQ44971HOL-6

HOL 4 - 600x1200 ONLY



IMQ44967HOL-4 IMQ44968HOL-4 IMQ44969HOL-4 IMQ44970HOL-4 IMQ44971HOL-4

	SIZE (MM)	THICKNESS		FINISHES		
1	1200x2600	6.5MM	-	NAT (R10) / PTV L ●	-	HOL-6 (R10)
2	1200x1200	6.5MM	10MM	NAT (R10) / PTV L ●	-	-
3	600x1200	-	10MM	NAT (R10) / PTV L ●	HAM (R11/B) / PTV L ●	HOL-4 (R10)
4	900x900	-	10MM	NAT (R10) / PTV L ●	-	-
5	450x900	-	10MM	NAT (R10) / PTV L ●	-	-
6	600x600	-	10MM	NAT (R10) / PTV L ●	-	-
7	300x600	-	10MM	NAT (R10) / PTV L ●	-	-
8	50x50 MOS on 300x300 MESH	-	10MM	NAT (R10) / PTV L ●	-	-
9	STEPTREAD 325x1200	-	10MM	NAT (R10) / PTV L ●	-	-
10	SKIRTING 60x1200 / 60x900 / 60x600 / 60x450	-	10MM	NAT / PTV L ●	-	-



PTV & LRV VALUES VARY BATCH TO BATCH PLEASE CONTACT FOR ADVICE. PRINT COLOURS MAY VARY, PLEASE REQUEST SAMPLES.

FIND US ON:



TECHNICAL SPECIFICATION

TECHNICAL CHARACTERISTIC	STANDARD	AVERAGE VALUES
Sizes	ISO 10545-2	Conforms
Water absorption	ISO 10545-3	<0.1%
Flexural resistance	ISO 10545-4	>45N/mm ²
Modulus of rupture	ISO 10545-4	1300N
Deep abrasion resistance	ISO 10545-6	<140mm ³
Deep abrasion resistance	ISO 10545-8	<7x10-6oC-1
Resistance to sudden temperature changes	ISO 10545-9	Resistant
Frost resistance	ISO 10545-12	Resistant
Resistance to chemical products	ISO 10545-13	GL
Slip resistance (Shod)	DIN 51130	NAT - R10 HAM - R11
Slip resistance (Barefoot)	DIN 51097	HAM - B
Pendulum test results	-	PTV L ● (Low slip potential)
Stain resistance	ISO 10545-14	Class 3

CLEANING + MAINTENANCE ADVICE

INITIAL WASHING

The initial washing is fundamental for good treatment results. The initial washing is aimed at removing any laying residues and building grime.

Product	Deterdek (1:5 diluted in water)
Coverage	Deterdek (5 l per 100m ²)
Equipment	Single-disc professional floor cleaner, liquid vacuum cleaner and cloth
Procedure	<ul style="list-style-type: none"> • After the floor is swept and soaked with water, spread the diluted Deterdek onto the floor. • Then scour with single-disc professional cleaner • Vacuum the residue, rinse the floor well and then mop with a liquid vacuum cleaner or a cloth.

ROUTINE MAINTENANCE

The aim of the routine maintenance is to remove dirt and scuff marks. Must be carried out regularly.

Product	Filacleaner (Diluted 1:50 in warm water)
Equipment	Cloth or mop (For large areas the use of a cleaning machine is recommended)
Procedure	<ul style="list-style-type: none"> • Dilute Filacleaner in warm water • Wipe a cloth wet with the solution over the floor • Rinse the floor in case of concentrated solutions of Filacleaner

SPECIAL MAINTENANCE

Special maintenance is carried out in case of very stubborn dirt, when the routine maintenance is not enough to restore the original look of the surface.

Product	Fila PS/87 (1:5 diluted in water)
Coverage	5 l per 100m ² (when diluted 1:5)
Procedure	<ul style="list-style-type: none"> • Dilute Fila PS/87 in 1:5 in water • Apply to the floor previously soaked with water and leave for a few minutes • Scrub with a single disc professional cleaner • Mop up residue with a liquid vacuum cleaner or cloth