GIBRALTAR

- Suitable for internal wall applications
- Handmade effect
- Crackle glaze
- Contains 55% recycled material and EPD verified



www.grestec.co.uk | T: +44 (0) 345 130 2241 | E: sales@grestec.co.uk

















ADN32503 LRV: 68



ADN32507 LRV: 10

ADN32527 LRV: 44

ADN32526 LRV: 47

ADN32504 LRV: 65





ADN32505

ADN32528 LRV: 44

ADN32506 LRV: 22



	SIZES (mm)	> <	FINISHES	ADN32503	ADN32505	ADN32507	ADN32527	ADN32526	ADN32504	ADN32528	ADN32506
1	75x300	9mm	CRACKLE GLAZE								
2	150x150	9mm	CRACKLE GLAZE								
3	75x150	9mm	CRACKLE GLAZE								
4	130x150 RODAPIE	9mm	CRACKLE GLAZE								
5	75x150 CORNISA	9mm	CRACKLE GLAZE								
6	75x150 HOJAS	9mm	CRACKLE GLAZE								
7	50x150 MOLDURA	9mm	CRACKLE GLAZE								
8	25x150 BARRA	9MM	CRACKLE GLAZE								









TECHNICAL SPECIFICATION

TECHNICAL CHARACTERISTIC	STANDARD	AVERAGE VALUES	AVERAGE VALUES		
Water absorption	ISO 10545-3	> 10% Group BLL			
Bending strength	ISO 10545-4	RM > 150 kg/cm ²	150 kg/cm ²		
Resistance to chemical products	ISO 10545-13	Resistant			
Stain resistance	ISO 10545-14	Resistant			
Crazing resistance	ISO 10545-11	Resistant			
Scratch hardness (MOHS scale)	EN 101	Gloss - hardness 4			

SUSTAINABILITY INFORMATION



MATERIAL	RECYCLED CONTENT	EPD	ISO 14001:2015 – ENVIRONMENTAL MANAGEMENT
Glazed porcelain tiles	55%	Yes	Yes



CLEANING + MAINTENANCE ADVICE

INITIAL WASHING

The initial washing is fundamental for good treatment results. The initial washing is aimed at removing any laying residues and building grime.

Equipment	Cloth
Procedure	 Clean off cement stains from grouting and other building work, which once hardened, will not be removed during any normal cleaning procedure.
	Clean wall tiling with a dry cloth when joints are hard.

ROUTINE MAINTENANCE

The aim of the routine maintenance is to remove dirt and scuff marks. Must be carried out regularly.

Product	Filacleaner (Diluted 1:50 in warm water)
Equipment	Cloth
Procedure	Remove dust with a dry cloth

· Wash with FilaCleaner using a cloth that should be soaked often in the solution and wrung out well



