





Formista

Formista blends the timeless charm of terracotta with the durability of modern porcelain stoneware. Featuring vibrant hues and soft, earthy tones, it captures nature's warmth and colour in a versatile, contemporary collection. Designed to inspire well-being and connection, Formistabrings a rich, grounded elegance to any space.



























PDEC54537 LRV: 44

PDEC54538 LRV: 20

PDEC54539 LRV: 39

LRV: 35

PDEC54540T1 PDEC54541T1 PDEC54542T1

LRV: 23







PDEC54543T3 PDEC54538T1









PDEC54540T2 PDEC54541T2 PDEC54542T2







Formista



Formats

Size (mm)		Thickness	PTV Wet Slider 96	PTV Wet Slider 55	Colour availability
1	1200x2780	6	Natural ≥ 36 PTV	-	All colours
2	1200x1200	9	Natural ≥36 PTV	-	All colours
3	600x1200	9	Natural ≥ 36 PTV	Hammered ≥38 PTV	All colours
4	600x1200	20	Thick	-	PDEC545 38, 39, 40
5	600x1200 T5	9	Natural	-	All colours
6	900x900	9	Natural ≥ 36 PTV	-	All colours
7	600x600	9	Natural ≥ 36 PTV	Hammered ≥38 PTV	All colours
8	600x600	20	Thick	-	PDEC545 38, 39, 40
9	300x600	9	Natural ≥ 36 PTV	Hammered ≥38 PTV	All colours
10	200x200 T1, T2, T3	9	Natural ≥ 36 PTV	-	All colours
11	50x50 mos on 300x300	9	Natural ≥ 36 PTV	-	All colours
12	50x150 mos on 300x300	9	Natural ≥ 36 PTV	-	All colours
13	300x1200 / 300x600 ST1	9	Natural ≥ 36 PTV	-	All colours
14	330x1200x40 ST2	9	Natural ≥ 36 PTV	-	All colours
15	330x1200x40 Corner	9	Natural ≥36 PTV	-	All colours
16	70x600 SK	9	Natural	-	All colours

Surface Roughness

Natural: Rz 31 Hammered: Rz 58



\Diamond

Formista



Above FormistaPDEC54541

Right Formista PDEC54543





Above Formista PDEC54539



Formista

Technical data sheet - ISO 10545 average values

2	Sizes	Very low tolerance
3	Water absorption	< 0,1%
4	Flexural strength	45 N/mm2
6	Deep abrasion resistance	≤150 mm³
8	Linear thermal expansion	6 x 10 ⁻⁶
12	Frost resistance	Conforms
13	Chemical resistance	A
14	Stain resistance	Class 4-5
	Pendulum test - Slider 96 (Shod) Wet	Natural ≥36PTV
	Pendulum test - Slider 55 (Barefoot) Wet	Hammered ≥38PTV

Sustainability information









Cleaning and maintenance advice

Initial washing

The initial washing is fundamental for good treatment results. The initial washing is aimed at removing any laying residues and building grime.

Product: Deterdek Pro

Routine maintenance

The aim of the routine maintenance is to remove dirt and scuff marks. Must be carried out regularly. Product: Cleaner Pro

Special maintenance

Special maintenance is carried out in case of very stubborn dirt, when the routine maintenance is not enough to restore the original look of the surface.

Product: PS/87 Pro

Please see www.filasolutions.com for methods of use, dilution and coverage.