ISO 13006 GROUP BIb
Water Absorption 0.5% to 3%

ISO 10545 Results

2	**Length and width** **Thickness** **Rectilinearity** **Rectangularity** **Flatness** **Surface quality**	0,6% ± 5% 0,5% 0,6% 0,5% 95% defect free
3	**Water absorption**	0.5% < Eb ≤ 3%
4	**Breaking strength (N) - Thickness ≥ 7,5mm** **Breaking strength (N) - Thickness < 7,5mm** **Modulus of rupture (N/mm2)**	≥ 1100 ≥ 700 ≥ 30
5	**Resistance to impact**	Available
7	**Resistance to abrasion**	Available
8	**Linear thermal expansion**	Available
9	**Resistance to thermal shock**	Available
10	**Moisture expansion**	Available
11	**Crazing resistance**	Required
12	**Frost resistance**	Required
13	**Resistance to low concentrations of acids and alkali** **Resistance to high concentrations of acids and alkali** **Resistance to chemical cleaning products**	Manufacturer declaration Available Min. GB
14	**Stain resistance**	Min Class 3
15	**Release of Lead and Cadmium**	Available



Cesano 0.5% < Eb ≤ 3% Water Absorption